



9th International Symposium on New Materials and Nano-Materials for Electrochemical Systems

XII International Congress of the Mexican Hydrogen Society

Mérida, Yucatán, México

July 9-13, 2012

BOOK OF ABSTRACTS



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

TABLE OF CONTENTS

00017 Study Annealing Effects On The Properties Of Electrodeposited CdSe Thin Films.....	1
00018 Comparative Electrochemical Characterization Of Pt/C And Pt-Au/C Catalysts Synthesized By Surface Redox Reactions	2
00019 Design and manufacture of a PEMFC stack using Pd5Cu4Pt/C as cathodic electrocatalyst.....	3
00020 Platinum Reduction Study On Pt/C As Electro-Catalysts For PEMFC.....	4
00023 Effects on Nafion® 117 membrane using different types of strong acids in various concentrations	5
00025 Application of RuXMoYSeZ for Oxygen Reduction Reaction in Cathode and Two Anodic Material on the Performance of Two Single Chamber Microbial Fuel Cells.....	6
00027 Microwave Synthesis of Ru3Pd6Pt as Cathode in PEM Fuel Cells	7
00028 Biohydrogen Production through Solid Substrate Fermentation of Organic Municipal Wastes: a Multivariable Evaluation.....	8
00030 Trnsys Hybrid System Simulation for Home Electrifying	9
00031 Implementation Of The Bem Theory To The Rotor Of A Small Wind Turbine Under Wind Conditions At Istmo De Tehuantepec.....	10
00032 Remediation of a Soil Contaminated with Lindane in an Electrobiochemical Slurry Reactor.....	11
00033 Ionic conduction on ABPBI/ benzimidazole/H3PO4 proton exchange membranes.....	12
00034 Capacitance Improvement of Carbon Aerogels by the immobilization of Polyoxometalates Nanoparticles	13
00035 Capacitance improvement based on cell design.....	14
00036 Comparison of a Chemical and an Electrochemical Enrichment Methods of a Saline Inoculum for Microbial Fuel Cells.....	15
00039 Kinetic Study of Pt- H3PMo12O40 for methanol electro-oxidation.....	16
00040 Origin of oxygen reduction activity on tantalum oxide-based compounds as non-platinum cathodes for PEFC.....	17
00041 Starch Assisted Sol Gel Synthesis of Birnessite for an Electrochemical Capacitor Application.....	18
00042 Biohydrogen production in fluidized bed bioreactors: room temperature vs 35°C	19
00043 Study Of The Electrochemical Grown Of Polyaniline By Using Different Electrolytic System.	20
00044 Electrocatalytic activity of Pt-Re /C catalysts for methanol electrooxidation	21
00045 Evaluation of pre-treatment on the first stage of an anaerobic digester for enhancing bio-hydrogen production and its associated Energy Balance	22
00047 Design, Manufacture And Evaluation Of A 250W PEM Fuel Cell Stack.....	23
00048 Electrochemical Activity of Pt/oxide-C Composites on the.....	24
00049 Performance improve of a PEM electrolyzer, decreasing the ohmic resistance because of manufacturing and assembly processes.....	25
00050 Performace Of Supercapacitors Based On Graphene Oxide And Mesoporous Carbon	26
00051 Oxygen reduction reaction on Pt/C electrocatalysts obtained	27
00052 Biohydrogen Production through Solid Substrate Fermentation of Organic Municipal Wastes: a Multivariable Evaluation.....	28
00053 Characterization of a five-face parallelepiped microbial fuel cell equipped with sandwich electrodes and analysis of microbial diversity of inócula.....	29
00054 Photodegradation of hydrocarbons using nanostructured TiO2/Cu powder.....	30
00055 Au@Pt core-shell type catalyst for hydrogen oxidation in presence of carbon monoxide	31
00056 Synthesis and properties of styrene ionic liquid copolymers for high temperature anhydrous fuel cells	32
00057 Methanol Electrooxidation on Au-Pd/C in Alkaline Media: The Dissolution of Palladium in the Bimetallic Alloy - A Case Scenario	33
00058 Electrocatalytic Properties of NiMo Nanoparticles for the Hydrogen Evolution Reaction.....	34



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

00059 Roadmap for hydrogen technology in urban public transport in the metropolitan area of Merida, Yucatan.....	35
00060 Electrochemical characterization of Ni-based Alloys at the hydrogen evolution zone in alkaline media	36
00061 C-TiO ₂ and C-ZrO ₂ composite supports for Pt electrocatalyst to evaluate in ethanol anodic oxidation	37
00062 Design of bipolar plates for a PEM electrolysis cell	38
00063 Effect of Sb- Doped SnO ₂ Supports Heat Treatment on the Oxygen Evolution Reaction.....	39
00064 Stack fuel cell prototype used to power a LED system.....	40
00065 Coke Gasification As An Alternative To Produce Hydrogen For A New Petroleum Refinery.....	41
00066 Evaluation and comparative analysis of Pt-Mo/C catalysts synthesized by different methods for application as anodes in direct methanol fuel cells.....	42
00067 Design and development of a Direct Ethanol Fuel Cell (DEFC) stack	43
00068 ZnO Electrodeposition & Application in Dye-Sensitized Solar Cells.....	44
00069 Sustainable Hydrogen Production in Yucatan.....	45
00070 Hydrogen Storage in Metal Organic Framework	46
00071 Influence Of The Properties Of TiO ₂ Nanomaterials On The Performance Of Dye-Sensitized Solar Cells.....	47
00072 A Dye-Sensitized Brookite Solar Cell	48
00073 Use Of A Tryfunctional Crosslinking Agent In Styrene/Acrylic Acid Copolymers To Enhance Mechanical Properties For Their Use As Membranes In Fuel Cells	49
00074 ZnO nanorods functionalized with TiO ₂ nanoparticles for application in dye-sensitized solar cells	50
00075 Synthesis and Luminescence Properties of Sulfonated Poly-{Styrene-co-Acrylic Acid}	51
00076 DNA Gold Modified Electrodes for HPV Detection.....	52
00077 Synthesis and Characterization of Pyrochlore and Perovkite Potassium Tantalates for Water Splitting.....	53
00078 Photocatalytic Hydrogen Evolution from Pure Water Using a New Sm ₂ GaTaO ₇ Advanced Compound.....	54
00079 Electrochemical And Capacitive Properties Of Polyaniline Evaluated In H ₂ SO ₄ And NaNO ₃ Systems.	55
00080 Graphene Oxide For Application In Supercapacitors No- Faradaic	56
00081 Development of Polymeric Enzymatic Electrodes for Ethanol Oxidation	57
00082 Preparation and Study of Polymeric Catalysts for Electrolysis.....	58
00083 Design and Construction of a Demonstrative Hybrid System Consisting of a Solar Panel, a Stack of Regenerative PEM Fuel Cells and Supercapacitors.....	59
00084 Experimental and theoretical studies of Cu/Ni-base catalysts for H ₂ generation.....	60
00085 Synthesis of NaTaO ₃ by a new solvo-combustion method and its hydrogen production photoactivity.....	61
00086 Unsupported Pt-Ru-Ir And Pt-Ir As Bi-Functional Catalyst For Reduction Oxygen And Oxygen Evolution Reactions In Acid Media.....	62
00087 Nanostructured Ferrite as Photocatalysts for H₂ Generation from Water Splitting and Sunlight	63
00088 Hydrogen Production by Steam Reforming of Ethanol over a Ru/Al ₂ O ₃ Catalyst.....	64
00090 Hydrogen Storage in Nanocomposite Materials of Polyaniline, Carbon Nanotubes and Titanium.....	65
00091 Development of a Low Power Backup System for Technology Demonstration	66
00092 Scooters electric motor characterization and the sizing of a PEMFC power plant required for its operation	67
00093 Development And Application Of Pt Black- Pt/IrO ₂ As Bifunctional Catalyst For URFC's.....	68
00E11 Design, Manufacture And Evaluation Of A 250W PEM Fuel Cell Stack	69
00E12 Feasibility Study To Use Hydrogen As Alternate Source Of Energy In Mexico.....	70
00E13 Microwave Assisted Polyol Synthesis of Nano-sized Pt and PtCr-based Electrocatalysts on Oxygen Reduction Reaction for PEM Fuel Cells.....	71
00E14 Life Cycle Assessment of Solar Selective Surfaces Produced by Continuous Electrochemical Process from Cradle to Grave	72
00E15 Towards the understanding and controlling of the photo-deposition of metal nanoparticles on oxides.....	73
00E16 Effect of the Selection of Material on the Electric Power Generation and Costs PEMFC Experimental Designs...	74



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

00E17 Theoretical studies of Sulfonated Poly (ether-imide): A Promising Material for Proton Exchange Membranes in fuel cells.....	75
00E19 Fast synthesis of M@Pt (M=Ru, Pd, Fe ₃ O ₄) core-shell nanostructures and their evaluation as anodes for the oxidation of ethanol.....	77
00E20 Synthesis of unsupported Pt-based electrocatalysts and evaluation of their catalytic activity for the ethylene glycol oxidation reaction	78
00E21 Integration of solar-hydrogen technologies for sustainable housing.....	79
00E22 Hydrogen adsorption in isorecticular MOF.....	80
00E23 Synthesis of Ag/Pt-Pd Core/Shell Nanoparticles and Their Electrocatalytic Properties towards the Oxygen Reduction Reaction.....	81
00E24 Effects on Nafion ® 117 membrane using different types of strong acids in various concentrations.....	82
00E25 C-TiO ₂ and C-ZrO ₂ composite supports for Pt electrocatalyst to evaluate in ethanol anodic oxidation	83
00E26 Design of bipolar plates for a PEM electrolysis cell.....	84
00E27 Desarrollo Y Aplicación De Membranas Hibridas Por El Proceso Sol – Gel Para El Enriquecimiento De Metano En Un Biodigestor Anaerobio.....	85
00E28 Study of the Ni/WOx-Hydrotalcite catalysts to produce hydrogen by ethanol steam reforming	86
00E29 Decentralized Energy Planning Using Multicriteria Methods	87
00E30 Synthesis and Characterization of Magnetic Barium Ferrite-Silica Nanocomposites.....	88
00E31 Electrical Transport Studies of the Solid Electrolyte system xAgI-(95-x)[2Ag ₂ O-B ₂ O ₃]-5TeO ₂ , where 45 ≤x≤65	89
00E32 Structural and magnetic studies of undoped and strontium doped lanthanum manganite system.....	90
00E33 Bimetallic materials based in Ag for cathode/anode electrode in a glucose microfluidic fuel cell	91
00E34 New BLi clusters capable of storing molecular hydrogen	92
00E35 Electrochemical Synthesis of Au and Pd Electrodes for Glucose Oxidation.....	93
00E36 Design and development of a Direct Ethanol Fuel Cell (DEFC) stack	94
00E37 2 nd Harmonic Voltammetry Electrochemical Technique For Palladium Synthesis Of Dendritic Structures.	95
00E38 Hydrogen Storage in Metal Organic Framework.....	96
00E39 Hydrogen Releasing Examination During The Reaction Of Aluminum At Al ₅ Fe ₂ Intermetallic Powders With Water	97
00E40 Evaluation of a ZrO ₂ composite membrane operating at High Temperature (100 °C) for Direct Methanol Fuel Cells.	98
00E41 Development of a Dynamic Hydrogen electrode coupled to a hydrogen proton exchange fuel cell.....	99
00E42 Synthesis of Pd/C and Pd/Pani for formic acid oxidation.....	100
00E43 Synthesis And Photoelectrochemical Characterization Of WO ₃ Nanomaterials.....	101
00E44 Theoretic-experimental study of Pd-based electrocatalyst for fuel cells.....	102
00E45 Tungsten Effect Over Co-hydrotalcite Catalysts to Produce Hydrogen from Bio-ethanol (Analysis of the catalyst structure).....	103
00E46 Pt Nanoparticles Supported on Carbon Nanotubes for Direct Ethanol Fuel Cells (DEFC) Application.....	104
00E47 High Performance Electroactivity in Pt/MWCNT and Pt/NiMWCNT Electrocatalysts.....	105
00E48 Characterization of a fuel cell unitized regenerative stack based on IrO ₂ -Pt/ATO as dual material.	106
00E49 Synthesis of Au-based materials with electrocatalytic properties for the glucosa electro-oxidation reaction.....	107
00E50 Design and implementation of a hybrid power system (wind-solar-fuel cell) of 4kW	108
00E51 Biological production of CO ₂ -free hydrogen by anaerobic microbial mixed microflora in an upflow anaerobic sludge blanket (UASB) reactor coupled with a gas purification device.	109
00E52 Photocatalytic water splitting for hydrogen production from N-TiO ₂ -X/Pt prepared by Nitrogen gas plasma (AC) method	110
00E53 Hydrogen Generation in a Microbial Electrolysis Cell (MEC) using two configurations: Catalyzed by Platinum and Biocathode.....	111
00E54 Progress on the PdP alloy deposition onto a gas diffusion layer for a PEMFC application.....	112



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

00E55	ORR kinetics on carbon paper-supported PdP cathodes: electrochemical impedance spectroscopy and rotating disk electrode study.....	113
00E56	Hydrogen Production by Solar Energy in Tropical Conditions	114
00E57	Electrocatalytic activity of Pt-Re /C catalysts for methanol electrooxidation.....	115
00E58	High Altitude Platforms (HAP's) powered by PEMFC's: a technological advantages review and analysis of their implementation in Quintana Roo, Mexico	116
00E59	Production And Purification Of Hydrogen Coupled To A Photovoltaic System.....	117
00E60	Preparation and Characterization of Pt-Pd and Pt-CeOx Electrocatalysts for the Oxygen Reduction Reaction in Absence and Presence of Metanol in Alkaline Medium	118
00E61	Thermodynamic Analysis of the Absorption Enhanced Autothermal Reforming of Ethanol.....	119
00E62	PREPARATION OF Coteta/MWCNT ORR ELECTROCATALYST.....	120
00E63	Absorption/Desorption Hydrogen Process In A Material Type Hidrotalcite	121
00E64	Platinum loading variation in MEAs to compare PEM Fuel Cell performance	122
00E65	Revisiting alkaline electrolysis: Challenges and opportunities for the production of hydrogen	123
00E66	Preparation and study on CoTETA/MWCNT catalyst as ORR electrocatalyst	124
00E67	Effect of carbon porosity on the electrochemical properties of carbon/polyaniline supercapacitor electrodes.....	125
00E68	Enhancement of oxygen reduction activity on carbon-supported Co-phthalocyanine modified with pyridine as nitrogen precursor in alkaline electrolyte.....	126
00E69	Studies of electrochemical properties and active sites of carbon-supported nickel phthalocyanine (NiPc/C) catalysts for oxygen reduction reaction.....	127
00E70	Carbon-supported copper phthalocyanine (CuPc/C) as novel cathode catalyst for polymer electrolyte membrane fuel cells --- Effect of Nafion ionomer as for alkaline electrolyte.....	128
00E71	High catalytic performance of Pt/C for the ethanol electrooxidation using sonochemically-treated XC-72R carbon support.....	129
00E72	Synthesis and evaluation of Pt-Sn/C and Pt/C nanomaterials for the ethanol oxidation reaction	130
00E73	Synthesis and Characterization of Pt-Au/C for Ethanol Tolerant ORR Electrocatalyst.....	131
00E74	Method for Water Electrolysis in Acid Medium.....	132
00E75	The Oxygen Reduction Reaction on Pt/TiOxNy Based Electrocatalyst for PEM Fuel Cell Applications.....	133
00E76	Correlation between the Physico-chemical Properties and the Oxygen Reduction Reaction electro catalytic activity in acid medium of Pd-Co Alloys synthesized by Ultrasonic Spray Method	134
00E77	Electrochemical investigation of Pd-Co thin films binary alloy for the oxygen reduction reaction in acid medium	135

**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

Nanostructured Ferrite as Photocatalysts for H₂ Generation from Water Splitting and Sunlight

Mercedes Yudith Ortega-López, Jesús Manuel Salinas-Gutiérrez, Alejandro López-Ortiz, Virginia Collins-Martínez*

Centro de Investigación en Materiales Avanzados S. C., Laboratorio Nacional de Nanotecnología, Depto. de
Materiales Nanoestructurados, Miguel de Cervantes 120, C. P. 31109, Chihuahua, Chih. México.

*Tel: +52 614 436 1129, Fax: +52 614 439 1130: e-mail: virginia.collins@cimav.edu.mx

ABSTRACT

Materials with higher efficiency and activated under the sunlight spectrum (band gap energy from 1.5 to 3.0eV) are today's trends in newer photocatalysts for the hydrogen generation. The aim of the present study is to investigate alternative semiconductor materials to titanium dioxide for the generation of hydrogen with band gap energy values lower than that of TiO₂ (<3.2eV). Examples of these are some transition metal ferrites such as CuFe₂O₄, CoFe₂O₄ and NiFe₂O₄. These ferrites were prepared by co-precipitation and heat treatment. Characterization was performed by XRD, BET, SEM, TEM and UV-Vis spectroscopy. Photocatalytic activity evaluation of the materials for hydrogen generation from water splitting under visible light was followed by gas chromatography. Results indicate that these materials showed corresponding spinel crystalline phases and nanometer particle sizes. Photocatalytic evaluation of these ferrites under visible light showed H₂ yields up to 10.8 mmol/g_{cat}. These yields compared with those reported in the literature indicate that these materials can be considered as promising photocatalysts for hydrogen generation.

Keywords: Ferrites, Nanoparticles, Photocatalytic activity, Water splitting



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

1. INTRODUCTION

The adverse environmental impact and the near depletion of fossil fuels, which are currently the preferred energy sources, represent the main motivations in seeking alternative energy sources from renewables. In this context, solar energy as an infinite resource [1] and the production of hydrogen as an energy carrier [2], are a clear option to clean, economical and sustainable energy generation through the use of fuel cells. In this context the hydrogen production from solar energy [3] and through the process of photocatalytic water-splitting represents a feasible clean energy alternative.

Within hydrogen production from photocatalytic water-splitting it is important to consider three main factors [3]: first, solar energy must be efficiently absorbed to generate pairs of electrons and holes for the dissociation of water, second, H_2 and O_2 recombination must proceed in order to reform the water molecule again and third, possible undesirable reactions may take place (corrosive reactions).

For the photocatalytic process to occur some conditions are needed to obtain a viable process. Since 1972, when Fujishima and Honda once successfully used by the first time TiO_2 photo-anodes in the evolution of hydrogen, while the use of semiconductor oxides has been considered a promising path for a sustainable hydrogen production [4]. From this fundamental study, an important amount of research has focused in finding alternate semiconductors to TiO_2 Degussa P25 (material usually used as a reference photocatalyst) with equal or better activity towards the hydrogen production under the UV or visible light irradiation. One of the main disadvantages that TiO_2 presents is that the energy needed for its activation is found under the UV light spectrum (~ 3.2 eV). Therefore, it is a reasonable strategy to explore other materials capable to be activated under the visible light spectrum and that present equal or better efficiencies towards the hydrogen production through the water splitting process.

One example of such materials is the ferrites, which have been considered as a novel option in photocatalytic processes.

Dentro de este grupo de materiales las ferritas han sido estudiadas como una opción novedosa como fotocatalizador. Entre sus principales características se encuentran sus excelentes propiedades magnéticas, alta conductividad electrónica, alta estabilidad térmica, su efectiva actividad catalítica [5], su resistencia a la corrosión [3] y sobre todo un ancho de banda prohibida que se encuentra dentro del espectro de luz visible (1.4 eV) [1]. Among their main features are their excellent magnetic properties, high electronic conductivity, high thermal stability, their effective catalytic activity [5], its corrosion resistance [3] and mostly a forbidden band gap energy within the range of visible light (1.4 eV) [1]. Therefore, the objective of the present research is aimed on the synthesis, characterization and



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

photocatalytic evaluation of ferrite nanoparticles towards the hydrogen production using methanol as sacrificial reagent under visible light irradiation.

2. EXPERIMENTAL

2.1. Synthesis

CuFe_2O_4 , CoFe_2O_4 and NiFe_2O_4 were prepared by the method of chemical co-precipitation using the corresponding metal nitrate solutions and NaOH as a precipitating agent followed by a thermal treatment (see Figure 1). Stoichiometric amounts of nano-hydrated ferric nitrate, 2.5 hydrated copper nitrate and hexa-hydrated cobalt and nickel nitrates were used to prepare the corresponding nitrate solutions [6]. Using a peristaltic pump, these nitrates were slowly added at a rate of 5 ml/min to the precipitating agent solution (NaOH). The reacting mixture was kept under constant stirring and a basic pH of 13 using NaOH under constant stirring. This basic pH was required to influence the precipitation reaction rate of the complex, since a highly alkaline medium generates smaller (precipitate) size particles [6]. In order to obtain a nanoparticulate crystalline material the resulting solution was dried and exposed to a low temperature thermal treatment at 250°C for 6 hours, followed by 1 hour at 350°C. This precipitate was the allowed to cool to room temperature. Finally, the product was washed with distilled water and ethyl alcohol to eliminate any residue, then filtered and dried at 80°C by 4 hours to follow its characterization and photocatalytic evaluation.




Figure 1. Procedure for the synthesis of CuFe_2O_4 , CoFe_2O_4 and NiFe_2O_4 nanoparticles through co-precipitation.

**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

2.2. Powder Characterization

Samples crystalline phase was determined by X-ray diffraction (XRD) using a PANalytical diffractometer model X'Pert PRO equipped with a X'Celerator detector. From the X-ray diffraction patterns information and through the use of the Scherrer equation, the crystal size of the materials was calculated. The specific surface area of the materials was estimated by N₂ physisorption using the BET technique on an Autosorb-1, Gas Sorption System (Quantachrome Corporation). The homogeneity in chemical composition of the samples was determined through dispersive X-ray spectroscopy (EDS) mapping using a detector coupled to a scanning electron microscope model 5800-LV Jeol JSM brand. The particle size of the materials and their morphology was determined by transmission electron microscopy (TEM) using a Philips CM-200. The light absorption spectrum of the materials was obtained through UV-visible spectroscopy (UV/Vis) by a Perkin Elmer spectrophotometer model Lambda 10 equipped with integrating sphere.

2.3. Photocatalytic Evaluation

Figure 2 shows a scheme of the experimental system employed for the photocatalytic evaluation of the materials, which consists of a photoreactor, artificial lighting and data collection analysis equipment. The photoreactor was built using a quartz tube with a 5 and 19 cm diameter and length, respectively where a suspension of each nanoparticle material (CuFe₂O₄, CoFe₂O₄ y NiFe₂O₄) was placed. Two aluminum flanges bolted together by threaded rods were used to close the tube and its sealing was achieved through neoprene o-rings. The radiation source used was a white light artificial mercurial lamp of 120 W, GE. Concentration of initial reagents and changes in gas phase composition within the photoreactor during the course of the experiments was determined by gas chromatography (GC) using a Clarus 500, Perkin Elmer, equipped with thermal conductivity (TCD) and flame ionization (FID) detectors arranged in series. The sampling of the gas was performed through a septum sampling port located on one side of the photoreactor and transferred to the GC by hand injection using a 1 ml special syringe for gases.



9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012




Figure 2. Experimental setup system for the photocatalytic evaluation of the nanomaterials.

The photoreactor was hermetically sealed and checked for leaks. The photocatalytic suspension consisted of a mixture of distilled water and ethanol as a sacrificial reagent (50:1 molar ratio) and 200 mg of photocatalyst, which was artificially, irradiated using a visible light lamp. Prior to the photocatalytic evaluation the reactor was covered to prevent it from light exposure and was subjected to constant stirring for 15 minutes in order to achieve good homogenization of the suspension in the photoreactor. The initial concentration of gases was evaluated by gas sampling of the gas phase within the photoreactor and analyzed by GC. Then the mercury lamp was turned on and a gap of seven inches was left between the lamp and the photoreactor reactor wall. Sampling was performed manually every hour to complete twenty two hours of irradiation. Analysis of the initial gas phase concentration and of changes in gas composition inside the reactor was performed by means of gas chromatography (GC, Perkin Elmer Clarus 500), compounds separation used a Carboxen 100 packed column coupled with a thermal conductivity detector (TCD). Product identification was achieved by determining the elution time with respect to pure reagent concentrations and the quantification was performed using calibration curves.

3. RESULTS AND DISCUSSION

3.1. X-ray Diffraction (XRD)

Figure 3 presents results of XRD characterization for samples CuFe_2O_4 , CoFe_2O_4 and NiFe_2O_4




Figure 3. XRD patterns of the ferrites studied in the present research study.

For the copper ferrite sample CuO and CuFe_2O_4 phases were found in the XRD diffractogram, while for the case of the cobalt ferrite sample only the CoFe_2O_4 phase was present and in the particular case of sample nickel ferrite two phases were found; Fe_2O_3 and NiFe_2O_4 . Haihua, et al 2009 [3] reported a diffraction pattern with the same phases as those for sample CuFe_2O_4 . Whereas, the cobalt ferrite diffraction pattern is consistent with the one reported by Hua, et al, 2008 [7].

3.2. Scanning Electron Microscopy (SEM)

Figure 4 shows SEM images of samples CuFe_2O_4 , CoFe_2O_4 and NiFe_2O_4 . In this Figure it can be observed that in all cases it can be observed agglomerated particles with irregular morphologies (spherical, flake-like or needle), which are in the order of nanometers. Here it can be concluded that a careful control of the nitrate addition during the precipitation process has a significant effect in obtaining nano-sized particles as can be seen in the SEM images [6].




Figure 4. SEM Images of (a) CuFe₂O₄, (b) CoFe₂O₄ and (c) NiFe₂O₄.

3.3. Transmission Electron Microscopy (TEM)

Morphology for the case of sample CuFe₂O₄ (see Figure 5a) is composed by agglomerate particles of irregular shapes with sizes varying between 15 and 30 nm, the same morphology was reported by Haihua, et al 2009 [3] for copper ferrites. While, for cobalt (b) and nickel (c) ferrites it can be observed sizes of around 25 nm. Here also, very similar particle sizes were reported by Hua et al, 2008 [7] for both kind of samples.




Figure 5. TEM images at 50kX for samples (a) CuFe₂O₄, (b) CoFe₂O₄ and (c) NiFe₂O₄.

3.4. BET Surface Area

It is well known that surface area is directly influenced by the particle size and at the same time closely related to the method of synthesis being employed. The specific surface areas of the photocatalysts were 32, 21 and 24 m²/g for samples CuFe₂O₄, CoFe₂O₄ and NiFe₂O₄, respectively.

Figure 6 shows the BET adsorption isotherms obtained for the synthesized samples in the present research. The above reported values of surface area can be explained in terms of the shapes of these isotherms. For the case of

**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

sample CuFe_2O_4 the presence of hysteresis and a type IV is an indication of a porous material, while samples CoFe_2O_4 and NiFe_2O_4 present type III isotherms with negligible hysteresis and consequently porosity.




Figure 6. BET adsorption Isotherms for samples (a) CuFe_2O_4 , (b) CoFe_2O_4 and (c) NiFe_2O_4 .

3.5. UV/Vis Spectroscopy

UV/Vis diffuse reflectance spectra for samples of CuFe_2O_4 , NiFe_2O_4 CoFe_2O_4 and are presented in Figure 7. Here, the edge energy of the forbidden band can be calculated from the reflectance data by the Kubelka-Munk function.




Figure 7. UV/Vis diffuse reflectance spectra from samples (a) CuFe_2O_4 , (b) CoFe_2O_4 and (c) NiFe_2O_4 .

From this Figure it can be observed that UV/Vis spectra for all samples fall within the visible light range. The band gap energy value for samples CuFe_2O_4 , CoFe_2O_4 and NiFe_2O_4 were 1.55, 2.05 and 1.94 eV, respectively. Therefore, it can be concluded that these materials presumably work as photocatalysts within the visible light spectrum. These values are consistent with the ones reported in the literature. For example, a value of 1.42 eV is reported for CuFe_2O_4 by Kezzim, et al 2011 [1], a band gap of ~ 1.5 eV for CoFe_2O_4 reported by Limei, et al 2011 [8], while a value of 2.19 eV for NiFe_2O_4 is reported by Erik, et al 2012 [9].

3.6. Photocatalytic Activity

Photocatalytic evaluation of the synthesized materials was carried out by follow up of the hydrogen production by gas chromatography.

Figure 8 show results from the photocatalytic evaluation of the synthesized materials. In this Figure, the hydrogen evolution in micro-mols per gram of catalyst ($\mu\text{m/g}_{\text{cat}}$) as a function of time is plotted for each tested photocatalyst. Here it can be seen that the superior performance of the ferrites with respect to TiO_2 (P25) is evident.




Figure 8. Hydrogen evolution profile for the synthesized materials as a function of time.

Otherwise, Table 1 show values of hydrogen evolution in micro-mols per gram of catalyst ($\mu\text{m/g}_{\text{cat}}$) after a total of 22 hours of reaction taken from results presented in Figure 8 and these are compared to TiO_2 (P25). The order from higher to lower hydrogen production was: $\text{NiFe}_2\text{O}_4 > \text{CoFe}_2\text{O}_4 > \text{CuFe}_2\text{O}_4$, which values were well above the obtained, for reference TiO_2 (P25). This behavior can be attributed to the fact that the ferrites are materials whose characteristics meet the conditions for carrying out the electron-hole pair reaction needed for good photocatalytic activity [9,10].

Table I. Hydrogen generation (%) as a function of time after 22 hours of irradiation



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

Material	H ₂ Evolution @ 22 h (μm/g _{cat})
TiO ₂ (P25)	1138
CuFe ₂ O ₄	2315
CoFe ₂ O ₄	2846
NiFe ₂ O ₄	3643

4. CONCLUSIONS

CuFe₂O₄, NiFe₂O₄ and CoFe₂O₄ nanoparticles were synthesized by a chemical co-precipitation method followed by heat treatment and tested for hydrogen production, demonstrating that the present synthesis technique is a simple, inexpensive and reproducible. For samples of NiFe₂O₄ and CuFe₂O₄ the dominant crystal structure is that of a spinel MeFe₂O₄ (Me = Cu, Ni) accompanied with formation of Fe₂O₃ and CuO, respectively. For the case of the CoFe₂O₄ sample the crystallographic structure of spinel CoFe₂O₄ is the only crystallographic phase present in the sample. SEM results indicate that in all cases nanoparticles were obtained with a wide variety of nanoscale morphologies ranging from spherical to flakes or needles. Photocatalytic evaluation towards hydrogen production resulted in a superior behavior of nickel, cobalt and copper ferrites compared to results obtained for reference TiO₂ (P25) photocatalyst. The order from higher to lower hydrogen production was: NiFe₂O₄ > CoFe₂O₄ > CuFe₂O₄. The good photocatalytic activity of the synthesized samples is related to the inherent properties of these materials, demonstrating that meet necessary conditions to carry out the electron-hole pair reaction required for good photocatalytic activity.

ACKNOWLEDGEMENTS

The authors are grateful to M Sc. Enrique Torres, M Sc. Karla Campos, Eng. Wilber Antunez, M Sc. Raul Ochoa and Eng. Luis de la Torre for their help on XRD, SEM, TEM, BET and UV-Vis spectroscopy characterization, respectively. Also to CIMAV, S. C and CONACYT for their financial assistance.



**9th International Symposium on New Materials and Nano-Materials for
Electrochemical Systems
XII International Congress of the Mexican Hydrogen Society
Merida, Mexico, 2012**

REFERENCES

- [1] A. Kezzim, N. Nasrallah, A. Abdi, M. Tari, Visible light induced hydrogen on the novel hetero-system $\text{CuFe}_2\text{O}_4/\text{TiO}_2$; *Energy Conversion and Management* 52 (2011) 2800–2806. 2800–2806.
- [2] N. Shimoda, K. Faungnawakij, R. Kikuchi, T. Fukunaga, K. Eguchi, Catalytic performance enhancement by heat treatment of CuFe_2O_4 spinel and γ -alumina composite catalysts for steam reforming of dimethyl ether; *Applied Catalysis A: General* 365 (2009) 71–78.
- [3] Haihua Yang, Jianhui Yan, Zhouguang Lu, Xiang Cheng, Yougen Tang, Photocatalytic activity evaluation of tetragonal CuFe_2O_4 nanoparticles for the H_2 evolution under visible light irradiation; *Journal of Alloys and Compounds* 476 (2009) 715–719.
- [4] Zhonghai Zhang, Md. Faruk Hossain, Takakazu Takahashi, Photoelectrochemical water splitting on highly smooth and ordered TiO_2 nanotube arrays for hydrogen generation; *International Journal of Hydrogen Energy* 35, 16 (2010) 8528–8535.
- [5] N.M. Deraz, Production and characterization of pure and doped copper ferrite nanoparticles/Pyrolysis; *J. Anal. Appl.* 82 (2008) 212–222.
- [6] M.Y. Ortega-López, J.M. Salinas-Gutiérrez, V. Guzmán-Velderrain, A López-Ortiz, V. Collins-Martínez, Alternate Semiconductor Materials to TiO_2 as Photocatalysts for the Degradation of Organic Compounds (2012).
- [7] Chaoquan Hua, Zhenghong Gao, Xiaorui Yang, One-pot low temperature synthesis of MFe_2O_4 ($\text{M} = \text{Co}, \text{Ni}, \text{Zn}$) superparamagnetic nanocrystals; *Journal of Magnetism and Magnetic Materials* 320 (2008) L70–L73.
- [8] Xue Limei, Zhang Fenghua, Chen Bin, Bai Xuefeng, Preparation of Light-Driven Spinel Nanoparticles CoAl_2O_4 , MgFe_2O_4 and CoFe_2O_4 and Their Photocatalytic Reduction of Carbon Dioxide; ISBN: 978-0-7695-4350-5 (2011).
- [9] Erik Casbeer, Virender K. Sharma, Xiang-Zhong Li, Review: Synthesis and photocatalytic activity of ferrites under visible light: A review; *Separation and Purification Technology* 87 (2012) 1–14.
- [10] Hong Deng, Hongyu Chen, He Li, Synthesis of crystal MFe_2O_4 ($\text{M} = \text{Mg}, \text{Cu}, \text{Ni}$) microspheres; *Materials Chemistry and Physics* 101 (2007) 509–513.

